



NO. OVRPK-HF009 V.2013



Shrink Film

OVR
P A C K A G I N G


An OVERITE company

OVR Shrink Film

OVR Shrink Film is multi-layer film with high tensile strength and available in a wide range of shrink film, and they has good shrink balance and hi-gross and transparency. We are able to any size as request of customers.

Also, protects packed product from prevents permeation of alien substance with strong bundling.

OVR Stretch film is an environment-friendly product that 100% recycling is possible.



PO Shrink film POF 12 μ m

Usage : Instant Foods Packaging

- Multi-layer film with high tensile strength.
- Wide range of shrinking & sealing temperature.
- Good shrink balance(MD/TD) and high gross & transparency.
- Wide selection of film according to customer's requirements.
- Non-toxic & environment friendly using approved materials by FDA.
- Cost effective by thinner & stronger film.



| Properties | Unit | Preliminary Value | | Standard of Test |
|-------------------------|--------------------|-------------------|-------|--|
| | | MD | TD | |
| Thickness | mm | 0.012 | | ASTM D374 |
| Haze | % | 2.1 | | ASTM D1003 |
| Gloss | % | 155 | | ASTM D2457 |
| Elongation | % | 130 | 110 | ASTM D882 |
| Tensile Strength | kg/cm ² | 1,250 | 1,260 | ASTM D882 |
| Shrinkage | % | 62 | 62 | Deposited in 120 $^{\circ}$ C glycerin for 20 sec. |
| Coefficient of friction | dynamic | 0.35 | 0.4 | ASTM D 1894 |

PO Shrink film POF 15 μ m

Usage : Drinks & Bundle Packing

- Multi-layer film with high tensile strength.
- Wide range of shrinking & sealing temperature.
- Good shrink balance(MD/TD) and high gloss & transparency.
- Wide selection of film according to customer's requirements.
- Non-toxic & environment friendly using approved materials by FDA.
- Cost effective by thinner & stronger film.



| Properties | Unit | Preliminary Value | | Standard of Test |
|-------------------------|--------------------|-------------------|-------|---|
| Thickness | mm | 0.015 | | ASTM D374 |
| Haze | % | 2.1 | | ASTM D1003 |
| Gloss | % | 155 | | ASTM D2457 |
| | | MD | TD | |
| Elongation | % | 130 | 110 | ASTM D882 |
| Tensile Strength | kg/cm ² | 1,250 | 1,260 | ASTM D882 |
| Shrinkage | % | 62 | 62 | Deposited in 120°C glycerin for 20 sec. |
| Coefficient of friction | dynamic | 0.35 | 0.4 | ASTM D 1894 |

PO Shrink film POF 20 μ m

Usage : Stationery Packing

- Multi-layer film with high tensile strength.
- Wide range of shrinking & sealing temperature.
- Good shrink balance(MD/TD) and high gloss & transparency.
- Wide selection of film according to customer's requirements.
- Non-toxic & environment friendly using approved materials by FDA.
- Cost effective by thinner & stronger film.



| Properties | Unit | Preliminary Value | | Standard of Test |
|-------------------------|--------------------|-------------------|-------|---|
| Thickness | mm | 0.020 | | ASTM D374 |
| Haze | % | 2.1 | | ASTM D1003 |
| Gloss | % | 155 | | ASTM D2457 |
| | | MD | TD | |
| Elongation | % | 130 | 110 | ASTM D882 |
| Tensile Strength | kg/cm ² | 1,250 | 1,260 | ASTM D882 |
| Shrinkage | % | 62 | 62 | Deposited in 120°C glycerin for 20 sec. |
| Coefficient of friction | dynamic | 0.35 | 0.4 | ASTM D 1894 |

PO Shrink film POS 15 μ m/20 μ m

Usage : Sundry goods & Heavy goods Packing

- Bi-oriented Multi-layer film, durable and strong.
- Wide sizes and wide range of shrinking & sealing temperature.
- Adaptable to any shapes with strong & perfect shrinkage.
- Compatible with most sealing equipments.
- Non-toxic & environment friendly using approved materials by FDA.
- Good shrink balance(MD/TD) and high gross & transparency.



| Properties | Unit | Preliminary Value | | Standard of Test |
|-------------------------|--------------------|-------------------|-------|--|
| Thickness | mm | 0.015 ~ 0.020 | | ASTM D374 |
| Haze | % | 2.5 | | ASTM D1003 |
| Gloss | % | 162 | | ASTM D2457 |
| | | MD | TD | |
| Elongation | % | 140 | 120 | ASTM D882 |
| Tensile Strength | kg/cm ² | 1,650 | 1,600 | ASTM D882 |
| Shrinkage | % | 75 | 75 | Deposited in 120 $^{\circ}$ C glycerin for 20 sec. |
| Coefficient of friction | dynamic | 0.35 | 0.4 | ASTM D 1894 |



*Best Quality, Cost effective products,
Best services for supply*

www.ovrpack.com



OVERITE INDUSTRIAL CO.LTD

*Head Office
3RA-526 Sihwa Industrial Complex,
1383-13 Jeongwang-dong, Siheung City
Gyeonggi Province, 429-854 South Korea.
Tel. +82-31-497-0366
Fax. +82-31-498-0367
Web site : www.overite.co.kr*

OVR
P A C K A G I N G

An OVERITE company